

#### Product description

ISO 1874-PA6 MNHS 14-050 GF15

Injection moulding grade, glass fibre-reinforced, heat stabilized, easy flowing, technical moulded parts with high rigidity and dimensional stability for use in construction of vehicles, electrical engineering, machine construction, building trade and in the field of leisure time articles

Application:

door handles, control elements, housing for relays, fans, radiator grill

#### Physical form and storage

The product is supplied dry and ready to use in moisture-proof packaging. The material is in the form of cylindrical or flat pellets. Its bulk density is about 0,7 g/cm<sup>3</sup>. Standard packs are the special 25 kg bag and the 1000 kg bulk container (octagonal IBC=intermediate bulk container made from corrugated board with a liner bag). Subject to agreement other forms of packaging and shipment in tankers by road or rail are also possible. All containers are tightly sealed and should be opened only immediately prior to processing. To ensure that the perfectly dry material delivered cannot absorb moisture from the air the containers must be stored in dry rooms and always carefully sealed again after some of the material has been withdrawn. Ultramid® can be stored for a longer period of time in dry, well vented rooms without any change to properties. After longer storage times (> 3 months for IBC or > 2 years for bags) or if material from previously opened containers is used, drying is recommended to remove absorbed moisture. Containers stored in cold rooms should be allowed to equalise to normal temperature so that no condensation forms on the pellets.

#### Product safety

In case processing is done under conditions as recommended (cf. processing data sheet) melts are thermally stable and do not generate hazards by molecular degradation or the evolution of gases and vapors. Like all thermoplastic polymers the product decomposes on exposure to excessive thermal load, e.g. when it is overheated or as a result of cleaning by burning off. Further information is available from the safety data sheet.

#### Note

The data contained in this publication are based on our current knowledge and experience. In view of the many factors that may affect processing and application of our product, these data do not relieve processors from carrying out their own investigations and tests; neither do these data imply any guarantee of certain properties, nor the suitability of the product for a specific purpose. Any descriptions, drawings, photographs, data, proportions, weights etc. given herein may change without prior information and do not constitute the agreed contractual quality of the product. It is the responsibility of the recipient of our products to ensure that any proprietary rights and existing laws and legislation are observed. In order to check the availability of products please contact us or our sales agency.

## Product Information

Typical values for uncoloured product at 23 °C <sup>1)</sup>	Test method	Unit	Values <sup>2)</sup>
<b>Properties</b>			
Polymer abbreviation	-	-	<b>PA6-GF15</b>
Density	ISO 1183	kg/m <sup>3</sup>	<b>1240</b>
Viscosity number (0.5% in 96 % H <sub>2</sub> SO <sub>4</sub> )	ISO 307, 1157, 1628	cm <sup>3</sup> /g	<b>145</b>
Water absorption, saturation in water at 23°C	similar to ISO 62	%	<b>8.2 - 8.7</b>
Moisture absorption, equilibrium 23°C/50% r.h.	similar to ISO 62	%	<b>2.00</b>
<b>Processing</b>			
Melting temperature, DSC	ISO 11357-1/-3	°C	<b>220</b>
Melt temperature, injection moulding/extrusion	-	°C	<b>270 - 290</b>
Mould temperature, injection moulding	-	°C	<b>80 - 90</b>
<b>Flammability</b>			
Automotive materials (Thickness >= 1mm) <sup>3)</sup>	FMVSS 302	-	<b>+</b>
<b>Mechanical properties</b>			<b>dry / cond.</b>
Tensile modulus	ISO 527-1/-2	MPa	<b>6000 / 3200</b>
Stress at break	ISO 527-1/-2	MPa	<b>120 / 75</b>
Strain at break	ISO 527-1/-2	%	<b>2.6 / 10</b>
Flexural modulus	ISO 178	MPa	<b>4500 / -</b>
Flexural strength	ISO 178	MPa	<b>180 / -</b>
Charpy unnotched impact strength (23°C)	ISO 179/1eU	kJ/m <sup>2</sup>	<b>35 / -</b>
Charpy unnotched impact strength (-30°C)	ISO 179/1eU	kJ/m <sup>2</sup>	<b>30 / -</b>
Charpy notched impact strength (23°C)	ISO 179/1eA	kJ/m <sup>2</sup>	<b>4 / -</b>
Charpy notched impact strength (-30°C)	ISO 179/1eA	kJ/m <sup>2</sup>	<b>3.5 / -</b>
<b>Thermal properties</b>			
HDT A (1.80 MPa)	ISO 75-1/-2	°C	<b>190</b>
HDT B (0.45 MPa)	ISO 75-1/-2	°C	<b>210</b>

### Footnotes

- 1) If product name or properties don't state otherwise.
- 2) The asterisk symbol "\*" signifies inapplicable properties.
- 3) + = passed

BASF SE

67056 Ludwigshafen, Germany